



Ottawa Hull K1A 0C9

(21) (A1)	2,178,056
(22)	1996/06/03
(43)	1996/12/08

(51) Int.Cl. ⁶ C08G 18/08; C08L 75/04

(19) (CA) APPLICATION FOR CANADIAN PATENT (12)

(54) Thermoplastic Polyurethane Elastomers

(72) Kirchmeyer, Stephan - Germany (Federal Republic of) ;
Müller, Hanns-Peter - Germany (Federal Republic of) ;
Ullrich, Martin - Germany (Federal Republic of) ;
Liesenfelder, Ulrich - Germany (Federal Republic of) ;

(71) Bayer Aktiengesellschaft - Germany (Federal Republic of)
;

(30) (DE) 19520732.7 1995/06/07

(57) 5 Claims

Notice: This application is as filed and may therefore contain an
incomplete specification.



THERMOPLASTIC POLYURETHANE ELASTOMERS

The present invention relates to thermoplastic polyurethane elastomers, to a process for the production thereof and to the use thereof.

5 Thermoplastic polyurethanes (TPU) are of significance because they have good elastomeric properties and may readily be melt processed. A very wide range of mechanical properties may be obtained by appropriate selection of the components. A review of TPU, their properties and applications may be found, for example, in *Kunststoffe* 68
10 (1978), pp. 819-825, *Kautschuk, Gummi, Kunststoffe* 35 (1982), pp. 569-584 and G. Becker, D. Braun *Kunststoff-Handbuch*, volume 7, *Polyurethane*, Munich, Vienna, Carl Hanser Verlag 1983. A review of production processes may be found in *Plastverarbeiter* 40 (1989).

TPU are mainly synthesized from linear polyols, such as polyester
15 or polyether polyols, organic diisocyanates and short-chain, mainly difunctional alcohols (chain extenders). They may be produced continuously or discontinuously. The best known production processes are the belt process and the extruder process.

In the belt process, the starting materials are metered into a
20 mixing head and vigorously mixed together in a very short period of time while they are still at a low viscosity. The reaction composition is then discharged onto a circulating steel or plastic belt on which the mixture reacts and solidifies with the addition of heat (GB-PS 1,057,018; DE-OS 3,224,324).

25 In the extruder process, the starting materials are together metered into a screw reactor, where they undergo polyaddition and are then converted into uniform pellets (US-PS 3,642,964; DE-PS 2,302,564; DE-PS 2,549,371; DE-OS 3,230,009; EP-OS 0,031,142).

The advantage of the belt process resides in the short mixing time for the starting materials and the subsequent shear-free and thus uninterrupted reaction. The resultant polyurethanes exhibit very good phase segregation and are particularly suitable for films. The

5 disadvantage of the belt process resides in the costly working up processes for the primary polymer sheets or strands obtained using this process. These do not have a uniform polymer structure and must subsequently be comminuted into homogeneous pellets and re-extruded.

10 In contrast, the extruder process is simple and low in cost, but the starting materials are not mixed until they reach the extruder under conditions in which polyaddition occurs. As a consequence, there are elevated concentrations of one component in certain areas of the extruder and unwanted and uncontrollable secondary reactions occur. Moreover, the polyurethanes are exposed to elevated shear forces
15 throughout the period of production. As a result, the phase segregation which occurs during polyaddition is severely disrupted and the resultant polyurethanes are only poorly suited to certain purposes, for example film production.

20 It is proposed in EP-A 0,554,718 and EP-A 0,554,719 to improve the extruder process by bringing the starting materials together in a nozzle and mixing them before they enter the extruder. Here too, the majority of the polyaddition reaction proceeds in the extruder, such that the TPU are exposed to severe shear forces during production and are thus damaged.

25 There is thus still considerable interest in TPU with improved properties and in processes which avoid the stated disadvantages in such a manner that polyurethanes may be produced in a controlled manner and with purposefully selected properties.

30 It has now been found that TPU having improved properties may be obtained in a process where the isocyanate is first mixed with the

isocyanat -reactiv component in a first static mixer to form a substantially unreacted reaction mixture and complete the reaction later in a second static mixer.

By means of this process, homogeneous TPU with greatly
5 improved properties compared with those of known processes are obtained. This was not expected.

The present invention provides a process for the production of thermoplastic polyurethane elastomers which comprises

(a) introducing and homogeneously mixing (A), (B) and optional
10 (C) in a first static mixer at a shear rate of 500 to 50000 s⁻¹ and at a temperature of 50 to 250 °C, to form a substantially unreacted mixture and

(b) reacting said substantially unreacted mixture in a second static mixer operating at a shear rate of 1 to 100 s⁻¹ and a temperature of 50 to
15 250 °C, to form a thermoplastic polyurethane elastomer, wherein (A) denotes one or more isocyanates, and where (B) denotes a mixture of (B1) and (B2) where B1 is 0 to 85 equivalent-% (relative to the isocyanate groups in (A)) of one or more compounds having an average of 1.8 to 3.0 Zerewitinoff active hydrogen atoms and a number average
20 molecular weight of 400 to 10000, and where B2 is 15 to 100 equivalent-% (relative to the isocyanate groups in (A)) of one or more chain extenders having an average of 1.8 to 3.0 Zerewitinoff active hydrogen atoms and a molecular weight of 62 to 400, and where (C) is a positive amount up to 20 % (relative to the weight of said thermoplastic polyurethane elastomer)
25 of conventional auxiliary additives.

The present invention furthermore provides the thermoplastic polyurethane elastomers obtained in this manner.

The present invention also provides the use of the thermoplastic polyurethane elastomers for the production of moldings (for example by
30 casting, compression molding, injection molding), such as sheets,

containers, equipment components, casings, rollers, gears, machinery and vehicle components, rolls, elastic coatings, blown and flat films, sheathing, tubes, catheters, seals, profiles, bearing bushes, threads, filaments and fibers.

- 5 Isocyanates (A) which may be used are aliphatic, cycloaliphatic, araliphatic, aromatic and heterocyclic polyisocyanates or any mixture of these polyisocyanates (c.f. Houben-Weyl, *Methoden der Organischen Chemie*, volume E 20, *Makromolekulare Stoffe*, Georg Thieme Verlag, Stuttgart, New York 1978, pages 1587-1593). Examples are ethylene
- 10 diisocyanate, 1,4-tetramethylene diisocyanate, 1,6-hexamethylene diisocyanate, 1,12-dodecane diisocyanate, 1,3-cyclobutane diisocyanate, 1,3- and 1,4-cyclohexane diisocyanate together with any desired mixtures of these isomers, 1-isocyanato-3,3,5-trimethyl-5-isocyanatomethyl-
- 15 cyclohexane, 2,4- and 2,6-hexahydrotolylene diisocyanate together with any desired mixtures of these isomers, hexahydro-1,3- and/or -1,4-phenylene diisocyanate, perhydro-2,4'- and/or -4,4'-diphenylmethane diisocyanate, norbornene diisocyanates (for example US-PS 3 492 330), 1,3- and 1,4-phenylene diisocyanate, 2,4- and 2,6-tolylene diisocyanate together with any mixture of these isomers, 2,4'- and/or 4,4'-diphenyl-
- 20 methane diisocyanate.

- Aromatic diisocyanates are preferred, in particular optionally alkyl-substituted tolylene and diphenylmethane diisocyanates, aliphatic diisocyanates, in particular hexamethylene diisocyanate and cycloaliphatic diisocyanates such as 1-isocyanato-3,3,5-trimethyl-5-isocyanato-
- 25 methylcyclohexane, perhydro-2,4'- and/or -4,4'-diphenylmethane diisocyanates.

- Isocyanates having a functionality greater than 2.0 to 3.0 may optionally also be used, such as 4,4',4''-triphenylmethane triisocyanate, polyphenyl/ polymethylene polyisocyanates (for example obtained by
- 30 aniline/formaldehyde condensation and subsequent phosphorylation),

together with the distillation residues which contain isocyanate groups which result during industrial isocyanate production, optionally in one or more of the above-stated polyisocyanates. However, care must be taken in this case to ensure that an average functionality of two is not exceeded if the polyurethanes are to be melt processed. It may be necessary to compensate for reactants with high functionality by using additional reactants with a functionality lower than two.

Monofunctional isocyanates suitable for this purpose are, for example, stearyl isocyanate, cyclohexyl isocyanate and phenyl isocyanate.

10 Zerewitinoff active compounds B1 are compounds having an average of 1.8 to 3.0 Zerewitinoff active hydrogen atoms and a number average molecular weight of 400 to 10000.

Such compounds include, as well as compounds containing amino groups, thiol groups or carboxyl groups, in particular compounds containing two to three, preferably two hydroxyl groups, especially those of a molecular weight of 450 to 6000, particularly preferably those of a molecular weight of 600 to 4500, for example polyesters, polyethers, polycarbonates and polyesteramides containing hydroxyl groups.

Suitable polyesters are, for example, reaction products of polyhydric, preferably dihydric and optionally also trihydric alcohols with polybasic, preferably dibasic carboxylic acids or the esterifiable derivatives thereof. The polycarboxylic acids may be aliphatic, cycloaliphatic, aromatic and/or heterocyclic, including halogen-substituted and/or unsaturated acids.

Examples of such carboxylic acids and the derivatives thereof which may be cited are: succinic acid, adipic acid, phthalic acid, isophthalic acid, phthalic anhydride, tetrahydrophthalic anhydride, hexahydrophthalic anhydride, tetrachlorophthalic anhydride, *endo*-methylenetetrahydrophthalic anhydride, maleic acid, maleic anhydride, fumaric acid, dimerised and trimerised unsaturated fatty acids, optionally mixed with monomeric unsaturated fatty acids, terephthalic acid dimethyl ester and terephthalic

acid bisglycol st r.

Polyhydric alcohols include ethylene glycol, 1,2- and 1,3-propylene glycol, 1,4- and 2,3-butylene glycol, 1,6-hexanediol, 1,8-octanediol, neopentyl glycol, 1,4-bis-(hydroxymethyl)cyclohexane, trimethylolpropane, trimethylolethane, together with di-, tri-, tetra- and higher polyethylene glycols, di- and higher polypropylene glycols, together with di- and higher polybutylene glycols. The polyesters may contain a proportion of terminal carboxyl groups. Polyesters prepared from lactones, for example ϵ -caprolactone, or from hydroxycarboxylic acids, for example ω -hydroxy-caproic acid, may also be used. It is, however, also possible to use hydroxy-functional polyesters known from fats chemistry, such as for example castor oil, and the transesterification products thereof.

Suitable polyethers are known *per se* and may be produced, for example, by the polymerization of epoxides, such as ethylene oxide, propylene oxide, butylene oxide, styrene oxide or epichlorohydrin or of tetrahydrofuran with itself, for example in the presence of Lewis catalysts such as boron trifluoride, or by the addition of epoxides, preferably of ethylene oxide and propylene oxide, optionally mixed or in succession, onto starter components with reactive hydrogen atoms such as water, alcohols, ammonia or amines, for example ethylene glycol, 1,3- or 1,2-propylene glycol, water, 4,4'-dihydroxydiphenyl-propane, aniline, ethanolamine or ethylenediamine.

Polycarbonates containing hydroxyl groups which may be considered are *per se* known polycarbonates which may be produced, for example, by the reaction of diols such as 1,3-propanediol, 1,4-butanediol and/or 1,6-hexanediol, diethylene glycol, triethylene glycol, tetraethylene glycol or thiodiglycol with diaryl carbonates, for example diphenyl carbonate, or phosgene (DE-OS 1,694,080, 2,221,751).

Suitable polyesteramides and polyamides include the predominantly linear condensation products obtained from polybasic saturated or

unsaturated carboxylic acids or the anhydrides thereof and polyfunctional, saturated or unsaturated amino alcohols, diamines, polyamines and the mixtures thereof.

Polyhydroxy compounds containing high molecular weight
5 polyaddition or polycondensation products or polymers in a finely dispersed, dissolved or graft-polymerized form are also suitable. Such modified polyhydroxy compounds may be obtained, for example, if polyaddition (for example reaction of polyisocyanates with amino-functional compounds) or polycondensation (for example of formaldehyde with
10 phenols and/or amines) is allowed to proceed in the presence of the compounds containing hydroxyl groups. Such processes are described, for example, in DE-AS 1,168,075 and 1,126,142, as well as DE-OS 2,324,134, 2,423,984, 2,512,385, 2,513,815, 2,220,796, 2,550,797, 2,550,833, 2,550,862, 2,633,293 and 2,639,254. It is, however, also possible
15 according to US-PS 3 869 413 or DE-OS 2 550 860 to mix an already-produced aqueous polymer dispersion with a polyhydroxy compound and then to remove water from the mixture.

Polyhydroxyl compounds modified by vinyl polymerization are also suitable, as are, for example, the ones obtained by the polymerization of
20 styrene and acrylonitrile in the presence of polyethers (US-PS 3,383,351, 3,323,093, 3,110,695, DE-AS 1,152,536) or polycarbonate polyols (DE-PS 1,769,795, US-PS 3,637,909). Polybutadienes containing hydroxyl groups are also suitable.

Naturally, mixtures of the above-stated compounds may also be
25 used, for example mixtures of polyethers and polyesters.

Zerewitinoff active compounds (B2) - chain extenders - have on average 1.8 to 3.0 Zerewitinoff active hydrogen atoms and a molecular weight of 62 to 400. These compounds are taken to include, as well as compounds containing amino groups, thiol groups or carboxyl groups,
30 those with two to three, preferably two hydroxyl groups.

- Exempl s of compounds (B2) ar di- and poly ls such as thyl ne glycol, 1,2- and 1,3-propylene glycol, 1,4- and 2,3-butylene glycol, 1,5-pentanediol, 1,6-hexanediol, 1,8-octanediol, neopentyl glycol, 1,4-bis(hydroxymethyl)cyclohexane, 2-methyl-1,3-propanediol, glycerol,
- 5 trimethylolpropane, 1,2,6-hexanetriol, trimethylolethane and pentaerythritol, di-, tri-, tetra- and higher polyethylene glycols with a molecular weight of up to 400, together with di- and higher polypropylene glycols with a molecular weight of up to 400, 4,4'-dihydroxydiphenol-propane, di(hydroxymethyl)-hydroquinone, ethanol-amine, diethanolamine, N-methyldiethanolamine,
- 10 triethanolamine and 3-aminopropanol; aliphatic diamines such as, for example, ethylenediamine, 1,4-tetramethylene-diamine, hexamethylenediamine, together with the mixtures thereof, 1-amino-3,3,5-trimethyl-5-aminomethyl-cyclohexane ("isophoronediamine"), 2,4- and 2,6-hexahydrotoluylene-diamine together with the mixtures thereof, perhydro-
- 15 2,4'- and -4,4'-diaminodiphenyl-methane, p-xylylene-diamine and bis-(3-aminopropyl)methylamine; aromatic diamines which may be cited are bisanthranilic acid esters, 3,5- and 2,4-diaminobenzoic acid esters, 3,3'-dichloro-4,4'-diaminodiphenylmethane, tolylenediamine and 4,4'-diaminodiphenylmethane.
- 20 Compounds which are monofunctional towards isocyanates may also be used in proportions of up to 2 wt.%, relative to the TPU, as chain terminators. Suitable compounds are, for example, monoamines such as butyl- and dibutylamine, octylamine, stearylamine, N-methylstearylamine, pyrrolidine, piperidine and cyclohexylamine, monoalcohols such as butanol,
- 25 2-ethylhexanol, octanol, dodecanol, the various amyl alcohols, cyclohexanol and ethylene glycol monomethyl ether.

The isocyanate-reactive compounds must be selected in such a manner that their average functionality does not exceed 2.0, if melt processable polyurethane elastomers are to be produced. If more highly

30 functional compounds are used, overall functionality must b r duced to

approximately 2 by the addition of monofunctional compounds.

The relative quantities of compounds (B1) and (B2) in (B) are preferably selected such that the ratio of the total of isocyanate groups in (A) to the total of Zerewitinoff active hydrogen atoms in (B) is 0.9:1 to

5 1.2:1.

The thermoplastic polyurethane elastomers according to the invention may contain as (C) preferably at most up to 20 wt. % (relative to the total quantity of TPU) of further conventional auxiliary substances and additives.

10 These include known catalysts, for example tertiary amines, such as triethylamine, N-methylmorpholine, N-ethylmorpholine, N,N,N',N'-tetramethyleneethylenediamine, pentamethyldiethylenetriamine, 1,4-diazabicyclo[2.2.2]octane, N-methyl-N'-dimethylaminoethylpiperazine (DE-OS 2 636 787), N,N-dimethylbenzylamine, N,N-dimethylcyclohexylamine, 2-
15 methy-limidazole, monocyclic and bicyclic amidines (DE-OS 1,720,633), bis-(dialkylamino)alkyl ethers (US-PS 3,330,782, DE-AS 1,030,558, DE-OS 1,804,361, 2,618,280), as well as tertiary amines which contain amide groups (preferably formamide groups) according to DE-OS 2,523,633 and 2,732,292. Other organic metal compounds, in particular
20 organic tin compounds, may also be used as catalysts. Organic tin compounds which may be considered, apart from compounds containing sulphur such as di-n-octyltin mercaptide (DE-AS 1,769,367, US-PS 3,645,927), are preferably tin(II) salts of carboxylic acids such as tin(II) acetate, tin(II) octoate and tin(II) laurate as well as tin(IV) compounds, such
25 as for example dibutyltin oxide, dibutyltin dilaurate or dioctyltin diacetate. Further compounds include titanium, bismuth and antimony compounds, such as for example antimony triisopropoxide, antimony octoate, antimony tallate, bismuth salts of carboxylic acids with 2 to 20 carbon atoms, such as bismuth trioctanoate, dibutylbismuth octanoate, triphenylbismuth
30 didecanoate and dibutyltitanium bis(acetylacetonate).

Further suitable catalysts are described in *Kunststoff Handbuch*, volume VII, *Polyurethane*, edited by Vieweg and Höchtlen, Carl Hanser Verlag, Munich 1966, for example on pages 96 to 102.

The total quantity of catalysts in the TPU according to the invention
5 is about 0 to 5 wt.%, preferably 0 to 2 wt.%, relative to the total quantity of TPU.

Further additives and auxiliary substances include: pigments, dyes, flame retardants such as tris(chloroethyl) phosphate, tricresyl phosphate or ammonium phosphate and pyrophosphate, stabilizers to counter the action
10 of ageing and weathering, plasticizers, lubricants and mould release agents, substances with a fungistatic and bacteriostatic action, as well as fillers such as calcium carbonate, silica gel, barium sulphate, calcium sulphate, kaolin, bentonite, zeolites, ground glass, glass beads, fibers of glass, plastic or carbon, silica sand or silica flour, silicon carbide, aluminum
15 trihydrate, chalk, dolomite or mixtures thereof.

In the first stage of the process, the starting compounds (A), (B) and (C) are mixed in a static mixer to form a substantially unreacted mixture. It is, however, permissible for up to 10 wt.%, preferably up to 5 wt.%, of the isocyanate groups present in the reactive mixture to react.

20 The isocyanates (A) may be used as monomeric di- or polyisocyanates or, alternatively, preferably as prepolymers. Prepolymers may be produced by reacting the entire quantity or a proportion of (A) with the entire quantity or a proportion of (B1), optionally in the presence of the auxiliary substances (C), at 30 to 220°C, preferably at 60 to 180°C,
25 particularly preferably at 100 to 160°C. The production of prepolymers containing isocyanate, the processing and use thereof is known in principle (see, for example, *Methoden der organischen Chemie* (Houben-Weyl), volume E 20, G. Thieme Verlag, Stuttgart, New York, 1987, pp. 1613-1617). The prepolymers may be produced discontinuously, for example in a
30 stirred tank, or continuously, for example using the processes described in

EP-A 0,571,828 or EP-A 0,571,831.

In case (A) is used as monomeric di- or polyisocyanates, (B1) is 20 to 85 equivalent-% (relative to the isocyanate groups in (A)) and (B2) is 15 to 90 equivalent-% (relative to the isocyanate groups in (A)).

5 The mixture leaving the first static mixer is passed through a second static mixer under conditions in which the reaction between (A) and (B) occurs. It is preferred that at least 40%, preferably at least 60%, most preferably 90% of the isocyanate groups in the reactive mixture will react. Conversion is principally dependent upon the temperature of the mixture in
10 the second static mixer and the residence time of the reactive mixture in the second static mixer. Conversion rises with rising temperature and rising residence time. It is possible to determine conversion on leaving the second static mixer, for example, by titrimetric determination, for example by reacting the isocyanate groups with an excess quantity of di-n-
15 butylamine and back-titrating with hydrochloric acid.

According to the invention, it is possible to use static mixers for both reaction stages as are, for example, described in *Chem.-Ing.-Techn.* 52, no. 4 on pages 285 to 291 and in *Mischen von Kunststoff und Kautschukprodukten*, VDI Verlag, Düsseldorf 1993.

20 Model SMX static mixers from the company Sulzer Chemtech, Winterthur, Switzerland are preferred. It is preferred for mixing purposes to use a static mixer having a shear rate of 100 s^{-1} to $100\,000 \text{ s}^{-1}$, particularly preferably of 500 s^{-1} to $50\,000 \text{ s}^{-1}$. It is furthermore preferred in stage 2 to use a static mixer having a shear rate lower than 100 s^{-1} , particularly
25 preferably, lower than 10 s^{-1} . A jet mixer may be used for rapid mixing of components (A) and (B).

The TPU leaving the second static mixer may optionally be further processed, for example by conditioning the polymer in sheet or block form, comminution or pelletizing in shredders or mills, degassing and pelletizing
30 with melting. The polymer is preferably passed through a unit for

continuous degassing and strand formation. This unit may be a multi-screw injection molding machine or extruder which is preferably equipped with but few, if any, kneading discs.

The TPU produced using the process according to the invention have markedly better mechanical and thermal properties than comparable polymers produced using prior art processes. This applies in particular to their elastic properties, such as elongation and tensile strength, and thermal properties such as heat resistance. The TPU according to the invention may be used in the conventional manner for the production of cast, compression molded and injection molded articles, thermoformed articles, semi-finished products, containers, equipment components, casings, rollers, gears, machinery and vehicle components, rolls, elastic coatings, blown and flat films, sheathing, tubes, catheters, seals, profiles, bearing bushes, threads, filaments and fibers. They may in general advantageously be used in applications where melt processable materials are used.

The following examples explain the invention in greater detail. All percentages are by weight, unless otherwise indicated.

EXAMPLES

20 Practical examples

Auxiliary substances used

Anti-oxidant: pentaerythritol tetrakis[3(3,5-di-tert.-butyl-4-hydroxy-phenyl)propionic acid ester],

Anti-hydrolysis agent: N,N'-methanetetrayl-2,6-bis(1-methylethyl)aniline,

25 Mould release agent: ethylenediamine bisstearylamine.

Example 1

Production of prepolymer 1

3000.0 g (1.33 mol) of a polyester prepared from adipic acid and butanediol having an number average molecular weight of 2250 g/mol are desiccated for 4 hours at 140°C and a pressure of 10 mbar in a 6 liter

thr -necked flask with a mechanical stirrer, internal thermometer and nitrogen inlet. 18.0 g of mould release agent, 3.0 g of anti-oxidant and 30.0 g of anti-hydrolysis agent are then added. The contents are cooled to 70°C, 1244.58 g (4.98 mol) of 4,4'-diphenylmethane diisocyanate are added, the temperature increased to 100°C after 10 minutes and stirring is continued for 2 hours at 100°C. A prepolymer having a titratable isocyanate content of 6.4% is obtained.

Production of the thermoplastic polyurethane elastomer

The reactor consists of two static mixers (SMX, Sulzer AG). Static mixer 1 has a diameter of 6 mm, a length of 35 mm and a shear rate of 500 s⁻¹. Static mixer 2 has a diameter of 34 mm, a length of 270 mm, a shear rate of 3 s⁻¹ and a heatable jacket, which is heated to 180°C. 5000 g/h of prepolymer 1 and 336.2 g/h of butanediol are continuously metered into the first static mixer. The mixture leaving static mixer 1 is passed into static mixer 2. The polymer melt leaving static mixer 2 is cooled and post-cured for 16 hours at 110°C. The comminuted polymer is converted into injection molded sheets and the properties of the injection molded sheets are determined.

Comparative example 1

TPU of an identical overall composition using the extruder process 5000 g/h of prepolymer 1 and 336.2 g/h of butanediol are continuously metered into the feed hopper of a conventional extruder. The temperature profile of the various barrel sections is as follows:

5

Barrel sec- tion	1	2	3	4	5	6	7	Die
Temp. in °C	180	200	200	200	200	180	170	180

The polymer strand is drawn off from the die, passed through a water bath, pelletized and post-cured for 16 hours at 110°C. Injection molded sheets are produced from the pellets and the sheet properties measured.

10 Properties

15

Polymer from example	Tear strength [MPa]	Elonga- tion at break [%]	Softening tempera- ture [°C]	Glass transition tempera- ture in [°C]	Shore A hard- ness
1	62	486	145	-24	86
Comari- son	40	450	120	-26	85

Example 1 shows that the tensile strength of the TPU according to the invention has been markedly increased in comparison with the comparative example.

20

Although the invention has been described in detail in the foregoing for the purpose of illustration, it is to be understood that such detail is solely for that purpose and that variations can be made therein by those skilled in the art without departing from the spirit and scope of the invention except as it may be limited by the claims.

The embodiments of the invention in which an exclusive property or privilege is claimed are defined as follows:-

1. A process for the production of thermoplastic polyurethane elastomer comprising

(a) introducing and homogeneously mixing (A), (B) and optional
5 (C) in a first static mixer at a shear rate of 500 to 50 000 s⁻¹ and at a temperature of 50 to 250 °C, to form a substantially unreacted mixture and

(b) reacting said substantially unreacted mixture in a second static mixer operating at a shear rate of 1 to 100 s⁻¹ and a temperature of 50
10 to 250 °C, to form a thermoplastic polyurethane elastomer, wherein (A) denotes one or more isocyanates, and where (B) denotes a mixture of (B1) and (B2) where B1 is 0 to 85 equivalent-% (relative to the isocyanate groups in (A)) of one or more compounds having an average of 1.8 to 3.0 Zerewitinoff active hydrogen atoms and a number
15 average molecular weight of 400 to 10000, and where B2 is 15 to 100 equivalent-% (relative to the isocyanate groups in (A)) of one or more chain extenders having an average of 1.8 to 3.0 Zerewitinoff active hydrogen atoms and a molecular weight of 62 to 400, and where (C) is a positive amount up to 20 % (relative to the weight of said
20 thermoplastic polyurethane elastomer) of conventional auxiliary additives.

2. The process of Claim 1 wherein (A) is a prepolymer containing isocyanate groups.

3. The process of Claim 1 wherein thermoplastic polyurethane
25 elastomer is continuously degassed and extruded.

4. The thermoplastic polyurethane elastomers produced according to the process of Claim 1.

5. The process of Claim 1 wherein the substantially unreacted mixture prepared in (a) contains at least 90 % by weight of the
30 unreacted components (A), (B1) and (B2).

2178056

L A 31 010

THERMOPLASTIC POLYURETHANE ELASTOMERS

ABSTRACT OF THE DISCLOSURE

A process for the production of thermoplastic polyurethane elastomer is disclosed. The process entails (a) introducing and homogeneously mixing in a first static mixer (A) an isocyanate and (B) a mixture of compounds having an average of 1.8 to 3.0 Zerewitinoff active hydrogen atoms having a molecular weight of 400 to 10000 with and chain extenders having an average of 1.8 to 3.0 Zerewitinoff active hydrogen atoms and a molecular weight of 62 to 400 and optional auxiliaries to form a substantially unreacted mixture and (b) reacting said substantially unreacted mixture in a second static mixer to form thermoplastic polyurethane elastomer. The elastomer thus produced has improved mechanical properties and is suitable for the production of moldings.